



# PRODUCT DATA SHEET

**STYREX® 335**

*Recycled Content High-Impact Polystyrene*

Resin Property	Unit	Value	ASTM Method
<b>Specific Gravity</b>	g/cm <sup>3</sup>	1.04	D792
<b>Vicat Softening Point</b>	°F	212	D1525
<b>Heat Deflection Temperature @66psi</b>	°F	185	Internal
<b>Rockwell Hardness</b>	“L” scale	47	D785
<b>Notched Izod Impact @73°F</b>	ft-lb/in	2.4	D256
<b>Tensile Modulus</b>	psi	330,000	D638
<b>Flexural Modulus</b>	psi	330,000	D790

**DISCLAIMER:**

All listed technical data are typical values intended for your guidance. Final testing and fitness for use are determined by the end customer and intended use. GOEX encourages customers to conduct their own test to determine physical properties.