

Resin Property	Unit	Values
Specific Gravity	g/cm ³	1.27
Vicat Softening Point	°F	185
Heat Deflection Temperature @66	psi	150
Light Transmission	%	87
Haze	%	1.1
Rockwell Hardness	"R" scale	106
Notched Izod Impact @73°F	ft-lb/in	1.1
Tensile Modulus	psi	210,000
Flexure Modulus	psi	210,000

DISCLAIMER:

All listed technical data are typical values intended for your guidance. Final testing and fitness for use are determined by the end customer and intended use. GOEX encourages customers to conduct their own test to determine physical properties.