

Resin Property	Unit	Values	ASTM Method
Specific Gravity	g/cm ³	1.39	D792
Vicat Softening Point	°F	177	Internal
Heat Deflection Temperature @66psi	°F	151	D648
Rockwell Hardness	“R” scale	78	D2240
Notched Izod Impact @73°F	ft-lb/in	20.9	D256
Tensile Modulus	psi	386,000	D638
Flexural Modulus	psi	430,000	D790

DISCLAIMER:

All listed technical data are typical values intended for your guidance. Final testing and fitness for use are determined by the end customer and intended use. GOEX encourages customers to conduct their own test to determine physical properties.