

Resin Property	Unit	Value	ASTM Method
Specific Gravity	g/cm ³	1.33	D792
Vicat Softening Point	°F	179	Internal
Heat Deflection Temperature @66 psi	°F	133	D648
Light Transmission	%	82	Internal
Rockwell Hardness	“R” scale	82	D2240
Notched Izod Impact @73°F	ft-lb/in	9	D256
Tensile Modulus	psi	372,000	D638
Flexural Modulus	psi	420,000	D790

DISCLAIMER:

All listed technical data are typical values intended for your guidance. Final testing and fitness for use are determined by the end customer and intended use. GOEX encourages customers to conduct their own test to determine physical properties.